

# BIANCOBIANCO

HOME COLLECTION

## EM MARBLE SPECIFICATION SHEET

**MANUFACTURER:** BIANCO BIANCO

**MATERIAL:** EM Marble

**AVAILABLE IN:**

**Thickness (mm):**

slabs 12, 20, 30, 40

tiles\* 12

**Thickness (inches):**

slabs ½", ¾", 1-¼", 1-½" (nominal)

tiles\* ½"

**Size (mm):**

slabs 3050 x 1240

tiles\* 300 x 300, 400 x 400, 600 x 600, 600 x 300, 500 x 300, 600 x 400

**Size (inches):**

slabs 120" x 48" (nominal)

tiles\* 12" x 12", 16" x 16", 24" x 24", 24" x 12", 20" x 12", 24" x 16" (nominal)

\* other sizes and thicknesses available upon request

**Finish:**

The material can be supplied in polished, honed, brushed or unpolished finish.

**Product description:**

Slabs and tiles in agglomerated marble made of 92-96% selected marble chips mixed with polyester resin.

**Color:**

Aggregates such as glass, mirror and mother of pearl can be added to the marble matrix. The shade is achieved by adding colored pigments with excellent stability to light. The material can be affected by acids and is quite soft, as all calcareous products.

**Standard:**

Standard EN 14617 "Agglomerated stone: Test methods"

Standard EN 15285:2008 "Agglomerated stone: Modular tiles for flooring and stairs (internal and external)"

Standard EN 15286:2013 "Agglomerated stone: Slabs and tiles for wall finishes (internal and external)"

**Eco-friendly certification:**

Due to the raw materials used and to the vibro-compression process, the material has achieved the "Greenguard Certification" (certificate n° 29305-410) and "Greenguard Gold Certification" (certificate n° 29305-420) issued by Greenguard Environment Institute. This means that the material can safely be used indoors, as its VOC emissions are well below the strict standard required by "Greenguard Gold Certification".

# BIANCOBIANCO

HOME COLLECTION

CHARACTERISTICS	STANDARD	VALUE	NOTES
Length and width	EN 14617-16	± 0,5 mm	Refers to tiles
Thickness	EN 14617-16	± 0,7 mm	Refers to tiles
Straightness of sides	EN 14617-16	± 0,3 mm	Refers to tiles
Rectangularity	EN 14617-16	± 0,9 mm	Refers to tiles
Center curvature	EN 14617-16	± 0,2% refers to length	Refers to tiles
Edge curvature	EN 14617-16	± 0,2% refers to length	Refers to tiles
Warping	EN 14617-16	± 0,2% refers to length	Refers to tiles
Apparent density	EN 14617-1	2450 - 2650 Kg/m <sup>3</sup>	
Water absorption	EN 14617-1	≤ 1,00%	
Flexural strength	EN 14617-2	10 - 35 MPa	
Abrasion resistance	EN 14617-4	33 - 44 mm	
Frost resistance	EN 14617-5	KM <sub>f25</sub> 0,4 - 1,2	
Thermal shock resistance	EN 14617-6	Δm% ≤ 0,15 % ΔR% ≤ 60 %	Test temperature: 70°C
Impact resistance	EN 14617-9	1,0 - 2,0 J 1,5 - 3,5 J	For thickness 12 mm For thickness 20 mm
Chemical resistance	EN 14617-10	C1	
Linear thermal expansion coefficient	EN 14617-11	12 - 26 x 10 <sup>-6</sup> °C <sup>-1</sup>	
Dimensional stability	EN 14617-12	Class A (<0,3 mm)	Class B (0,3 – 0.6 mm) for Green Plutone and Red Stone
Electrical resistivity	EN 14617-13	R <sub>s</sub> ≥ 1010 Ω R <sub>v</sub> ≥ 108 Ω m	Refers to surface Refers to volume
Compression resistance	EN 14617-15	90 - 150 MPa	
Mohs hardness	EN 101	up to 3 Mohs	
Thermal conductivity	EN 12524	1,3 W/(m K)	From tabulated values
Reaction to fire	EN 13501-1	A2 <sub>fl</sub> -s1	
Slip resistance	EN 14231	≥ 35 (Dry) ≥ 3 (Wet)	
Slip resistance	DIN 51130	R9	For honed H9